


\*\*\* AWTA TEXTILE TESTING \*\*\*  
REFERENCE SAMPLE

AWTA PROJECT NO : 168087.5-BV  
CLIENT: WARWICK FABRICS AUST PTY LTD  
CLIENT ORDER: SAMPLE:



# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd – trading as AWTA Product Testing

A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O. Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

CLIENT : WARWICK FABRICS AUST PTY LTD  
6-10 SACKVILLE STREET  
COLLINGWOOD VIC 3066

TEST NUMBER : 7-560041-BV  
DATE : 05/06/2008

SAMPLE DESCRIPTION Clients Ref: "Beachcomber"  
Woven fabric with knit backing  
Colour: Brown  
Enduse: upholstery

THESE RESULTS MUST BE CONSIDERED IN CONJUNCTION  
WITH THE COMMENTS ON THE FOLLOWING PAGE(S)

Material Specification provided by client:

Nominal composition: 100% polyester

Nominal mass: 598g/m2

AS/NZS  
1530.3 - 1999

Simultaneous determination of Ignitability, Flame  
Propagation, Heat Release and Smoke Release

RESULTS:

Face tested: Face

Date tested: 08/05/2008

	Mean		Standard Error
Ignition time	9.22	min	0.35
Flame propagation time	Nil	s	Nil
Heat release integral	56.4	kJ/m2	4.3
Smoke release, log d	-0.8358		0.0481
Optical density, d	0.1501	/m	

Number of specimens ignited: 6

Number of specimens tested: 6

REGULATORY INDICES:	Ignitability Index	11	Range 0-20
	Spread of Flame Index	0	Range 0-10
	Heat Evolved Index	2	Range 0-10
	Smoke Developed Index	5	Range 0-10

168087

2

(CONTINUED NEXT PAGE)

PAGE 1

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:

- Chemical Testing of Textiles & Related Products	:	Accreditation No. 983
- Mechanical Testing of Textiles & Related Products	:	Accreditation No. 985
- Heat & Temperature Measurement	:	Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



0204/11/06

*Sandolac*  
APPROVED SIGNATORY

*Michael A. Jackson*  
MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR



# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd – trading as AWTA Product Testing  
A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O. Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

CLIENT : WARWICK FABRICS AUST PTY LTD  
6-10 SACKVILLE STREET  
COLLINGWOOD VIC 3066

TEST NUMBER : 7-560041-BV  
DATE : 05/06/2008

### Comments:

These results only apply to the specimen mounted, as described in this report.

The results of this fire test may be used to directly assess fire hazard, but it should be recognized that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backing board at four points each 100mm from the centre of the sample and the assembly clamped in four places.

### Comments:

These results only apply to the specimen mounted, as described in this report.

The results of this fire test may be used to directly assess fire hazard, but it should be recognized that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The specimens melted away from the area of maximum heat and produced flaming droplets during the test. Due to this phenomena it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

168087

(CONTINUED NEXT PAGE)

PAGE 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:

- Chemical Testing of Textiles & Related Products	:	Accreditation No. 983
- Mechanical Testing of Textiles & Related Products	:	Accreditation No. 985
- Heat & Temperature Measurement	:	Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR



# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd – trading as AWTA Product Testing  
A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O. Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

CLIENT : WARWICK FABRICS AUST PTY LTD  
6-10 SACKVILLE STREET  
COLLINGWOOD VIC 3066

TEST NUMBER : 7-560041-BV  
DATE : 05/06/2008

AS 1530.2-1993

Test for Flammability of Materials

DATE TESTED: Flammability Index: 8 Range 0 - 100 for most material

05/06/2008

	Length	Width	
Spread Factor: Range 0 - 40	7	6	
Heat Factor: Range 0 - upward	1	1	
Maximum height (d) mean	6.1	5.7	
cv	5.5	15.2	%
Time (t) mean	n/a	n/a	s
cv	n/a	n/a	%
Heat (a) mean	3.7	1.9	degC min
cv	38.0	39.5	%
No of specimens tested	9	9	

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use

168087

PAGE 3

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:

- Chemical Testing of Textiles & Related Products	:	Accreditation No. 983
- Mechanical Testing of Textiles & Related Products	:	Accreditation No. 985
- Heat & Temperature Measurement	:	Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR