

BRIXHAM

Specifications

Collection(s)	Arlington
Colour(s)	Chai, Cornflower, Dove, Duckegg, Onyx, Paprika
Warwick Brand	Halo
Usage	Drapery / Heavy Commercial
Composition	100% Polyester
Pattern match	Yes
Pattern repeat (cm)	H: 13 x V: Stripe
Railroaded	No
Continuous	No
Lead weighted	No
Width (cm)	140
Weight (gsm)	568
Origin	Non EU
Stain Repellent	No
FIAA Care Label*	FW
WCAA Care Label*	4

*Please refer to Warwick Price List or Website www.warwick.co.nz

Test Results

Abrasion	
Martindale (ISO 12947, 12kPa)	150,000 Cycles
Seam slippage (mm)	
(ISO 13936-2, Load 180)	Warp 4.8, Weft 5.6
Pilling resistance	
(ISO 12945-2)	3/4
Colourfastness to light	
Xenon arc (ISO 105-B02, blue std 6)	>6
Colourfastness to rubbing	
(ISO 105-X12)	Dry 5, Wet 5
Dimension change - laundering (%)	
(ISO 5077/ISO 6330. 7BA)	Warp -0.7, Weft -1.2
Dimension change - hanging (%)	
(AS2663.1.B)	Warp 0.4, Weft 0.4
Free and Hydrolysed formaldehyde	
(ISO 14184-1:1998)	Not Detectable
Flammability AS/NZS 1530.2-1993	
Flamability Index (0 - 100)	-
Spread Factor (0 - 40)	Length -, Width -
Heat Factor (0 - upward)	Length -, Width -
Flammability AS/NZS 1530.3-1999	
Ignitability (0 - 20)	10
Spread of flame (0 - 10)	0
Heat evolved (0 - 10)	2
Smoke developed (0 - 10)	5

