

Specifications

Collection(s)	Mauritius
Colour(s)	Cascade, Cobalt, Forest, Jet, Lobster, Melon, Navy, Ocean, Palm, Pewter, Port, Sand, Stone, Sunshine
Warwick Brand	Halo, Sundec
Usage	General Domestic
Composition	100% Polypropylene
Pattern match	Yes
Pattern repeat (cm)	H: 35 x V: 15
Railroaded	No
Continuous	No
Lead weighted	No
Width (cm)	140
Weight (gsm)	303
Origin	Non EU
Stain Repellent	Fluro Chem
FIAA Care Label*	S
WCAA Care Label*	

*Please refer to Warwick Price List or Website www.warwick.co.nz

Test Results

Abrasion Martindale (ISO 12947, 12kPa)	15000-20000 Cycles
Seam slippage (mm) (ISO 13936-2, Load 180)	Warp 4.3, Weft 4.0
Pilling resistance (ISO 12945-2)	5
Colourfastness to light Xenon arc (ISO 105-B02, blue std 6)	>7
Colourfastness to rubbing (ISO 105-X12)	Dry 5, Wet 5
Dimension change - laundering (%) (ISO 5077/ISO 6330. 7BA)	Warp -0.6, Weft -0.3
Dimension change - hanging (%) (AS2663.1.B)	Warp 0.2, Weft 0.2
Free and Hydrolysed formaldehyde (ISO 14184-1:1998)	Not Detectable
Flammability AS/NZS 1530.2-1993 Flamability Index (0 - 100)	-
Spread Factor (0 - 40)	Length -, Width -
Heat Factor (0 - upward)	Length -, Width -
Flammability AS/NZS 1530.3-1999 Ignitability (0 - 20)	16
Spread of flame (0 - 10)	0
Heat evolved (0 - 10)	0
Smoke developed (0 - 10)	3