

PLINTH

Specifications

Collection(s)	Plinth
Colour(s)	Ash, Chocolate, Cobalt, Driftwood, Dusk, Grapefruit, Ivory, Lime, Linen, Manuka, Mocha, Ocean, Orchid, Pebble, Pine, Pomegranate, Slate, Stone, Strawberry
Warwick Brand	-
Usage	Drapery / Heavy Commercial
Composition	59% Acrylic 23% Polyester 13% Viscose 5% Linen
Pattern match	No
Pattern repeat (cm)	Plain
Railroaded	Plain**
Continuous	No
Lead weighted	No
Width (cm)	140
Weight (gsm)	583
Origin	Non EU
Stain Repellent	No
FIAA Care Label*	3
WCAA Care Label*	2

*Please refer to Warwick Price List or Website www.warwick.co.nz

**Fabrics marked Railroaded 'Plain' can be cut in either direction at the discretion of the manufacturer, and in consultation with the customer's preference. Fabric is sampled in the direction it comes up the roll (Non Railroaded).

Test Results

Abrasion	
Martindale (ISO 12947, 12kPa)	66,500 Cycles
Seam slippage (mm)	
(ISO 13936-2, Load 180)	Warp 5, Weft 4.5
Pilling resistance	
(ISO 12945-2)	4
Colourfastness to light	
Xenon arc (ISO 105-B02, blue std 6)	>6
Colourfastness to rubbing	
(ISO 105-X12)	Dry 5, Wet 5
Dimension change - laundering (%)	
(ISO 5077/ISO 6330. 7BA)	Warp -4.9, Weft -0.7
Dimension change - hanging (%)	
(AS2663.1.B)	Warp 0.9, Weft 0.4
Free and Hydrolysed formaldehyde	
(ISO 14184-1:1998)	Not Detectable
Flammability AS/NZS 1530.2-1993	
Flamability Index (0 - 100)	-
Spread Factor (0 - 40)	Length -, Width -
Heat Factor (0 - upward)	Length -, Width -
Flammability AS/NZS 1530.3-1999	
Ignitability (0 - 20)	-
Spread of flame (0 - 10)	-
Heat evolved (0 - 10)	-
Smoke developed (0 - 10)	-



COMMERCIAL TEXTILE ASSOCIATION
OF AUSTRALIA & NEW ZEALAND
LIMITED



Tested for harmful substances
according to Oeko-Tex Standard 100
HKC 23567 TESTEX
1505024 CENTEXBEL

